



Test Method C-650

Standard Test Method for Determining the Resistance of Ceramic Tile to Chemical Substances

This test measures the resistance of ceramic tile glaze to acid, alkali, and chemical agents.

This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Silestone® Results:	Stain Resistance (ASTM C-650)	
	Acetic acid (98%)	No effect
	Acetone	No effect
	Ammonium Hydroxide (28%)	No effect
	Benzene	No effect
	Butyl Alcohol	No effect
	Carbon Tetrachloride	No effect
	Ethyl Acetate	No effect
	Ethyl Ether	No effect
	Formaldehyde	No effect
	Hydrochloric Acid	No effect
	Phosphoric Acid (85%)	No effect
	Sulfuric Acid (33%)	No effect
	Xylene	No effect
	Zinc Chloride	No effect